

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 December 2001 (06.12.2001)

PCT

(10) International Publication Number
WO 01/91901 A1

- (51) International Patent Classification⁷: **B01J 35/10**, 29/12, C07C 2/58
- (21) International Application Number: PCT/EP01/05845
- (22) International Filing Date: 21 May 2001 (21.05.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
00201917.2 30 May 2000 (30.05.2000) EP
- (71) Applicant: **AKZO NOBEL N.V.** [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).
- (72) Inventors: **VAN BROEKHOVEN, Emanuel, Hermanus**; Trintel 131, NL-1141 DN Morinickendam (NL). **MAS CABRÉ, Francisco, René**; Max Havelaarlaan 30, NL-1183 NE Amstelveen (NL).
- (74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel N.V., Intellectual Property Department (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: NOVEL ALKYLATION CATALYST AND ITS USE IN ALKYLATION

(57) Abstract: The invention pertains to a catalyst comprising catalyst particles comprising a hydrogenation function and a solid acid, wherein the ratio between (i) the volume in catalyst pores with a diameter of 40 - 8000 nm and (ii) the specific length of the catalyst particles is in the range of 0.01 - 0.90 ml/(μ m) and wherein the catalyst has a total pore volume of at least 0.20 ml/g. The invention further pertains to the use of this catalyst in the alkylation of hydrocarbons. In the examples Pt/USY is used as catalyst.

WO 01/91901 A1

Novel alkylation catalyst and its use in alkylation

- 5 The present invention relates to a novel alkylation catalyst and the use thereof for the alkylation of hydrocarbons.

Within the framework of the present invention, the term alkylation refers to the reaction of a hydrocarbon, such as an aromatic or a saturated hydrocarbon,
10 with an olefin. Without limiting the scope of the invention we will further illustrate the invention by discussing the alkylation of saturated hydrocarbons, in general branched saturated hydrocarbons, with an olefin to give highly branched saturated hydrocarbons with a higher molecular weight.

This reaction is of interest because it makes it possible to obtain, through the
15 alkylation of isobutane with an olefin containing 2-6 carbon atoms, an alkylate which has a high octane number and which boils in the gasoline range. Unlike gasoline obtained by cracking heavier petroleum fractions such as vacuum gas oil and atmospheric residue, gasoline obtained by alkylation is essentially free of contaminants such as sulphur and nitrogen and so has clean burning
20 characteristics. Its high anti-knock properties, represented by the high octane number, lessen the need to add environmentally harmful anti-knock compounds such as lead. Also, unlike gasoline obtained by reforming naphtha or by cracking heavier petroleum fractions, alkylate contains few if any aromatics or olefins, which, environmentally speaking, is a further advantage.

25

The alkylation reaction is acid-catalyzed. At present, in commercial alkylation equipment use is made of liquid acid catalysts such as sulphuric acid and hydrogen fluoride. The use of such catalysts is attended with a wide range of problems. For instance, sulphuric acid and hydrogen fluoride are highly
30 corrosive, so that the equipment used has to meet high quality requirements. Since the presence of highly corrosive materials in the resulting fuel is

CONFIRMATION COPY

objectionable, the remaining acid has to be removed from the alkylate. Also, because of the phase separations which have to be carried out, the process is complicated and thus expensive. Besides, there is always the risk that toxic substances such as hydrogen fluoride will be emitted.

5

A newer development in this field is the use of solid acid catalysts, such as zeolite-containing catalysts. Thus WO 9823560 describes the use of a catalyst containing a zeolite, such as a Y zeolite, and a hydrogenation function, such as a Group VIII noble metal, e.g., platinum or palladium, and, optionally, a matrix material, such as alumina, in the alkylation of saturated hydrocarbons. Though the performance of this catalyst is satisfactory, there is still a need for further increase of catalytic activity, selectivity, and stability of these catalysts.

It has now surprisingly been found that the performance can be further improved by choosing the catalyst features such that (a) the ratio between (i) the volume in catalyst pores with a diameter in the range of 40 - 8000 nm and (ii) the specific length of the catalyst particles is in the range of 0.01 - 0.90 ml/(g*mm), (b) the total pore volume of the catalyst is at least 0.20 ml/g and (c) the volume in the catalyst pores with a diameter in the range of 40-8000 nm is below 0.30 ml/g.

The invention will be explained in more detail below.

The present invention pertains to a catalyst suitable for use in the alkylation of hydrocarbons which comprises catalyst particles comprising a hydrogenation function and a solid acid, wherein the ratio between (i) the volume in catalyst pores with a diameter in the range of 40 - 8000 nm and (ii) the specific length of the catalyst particles is in the range of 0.01 - 0.90 ml/(g*mm) and wherein the catalyst has a total pore volume of at least 0.20 ml/g and the volume in the catalyst pores with a diameter in the range of 40-8000 nm is below 0.30 ml/g.

In the following the pores having a diameter in the range of 40 - 8000 nm will be denoted "macropores" and the pore volume in these pores will be designated as "macropore volume".

- 5 The specific length of the catalyst particle is defined as the ratio between the geometric volume and the geometric surface of the solid part of this catalyst particle. The determination of the geometric volume and the geometric surface is known to the person skilled in the art and can be carried out, e.g., as described in DE 2354558. It is noted that the specific length is different from the
- 10 diameter of the catalyst particle. E.g., for a cylindrical catalyst particle the particle diameter is four to six times higher (depending on the diameter and the length of the particle) than the specific length. Further, the diameter of, e.g., a sphere is six times higher than the specific length.
- 15 As stated above, it is essential to the catalyst of the present invention that it has a ratio between macropore volume and specific length in the range of 0.01 - 0.90 ml/(g*mm). As further stated above, it is essential to the catalyst of the present invention that it has a total pore volume of at least 0.20 ml/g and that the macropore volume is below 0.30 ml/g
- 20 As is shown in the (comparative) examples below, the catalyst shows a significantly poorer performance in the alkylation of hydrocarbon feeds if the ratio between macropore volume and specific length and/or the total pore volume is outside these ranges.
- 25 Preferably, the ratio between macropore volume and specific length is above 0.20 ml/(g*mm), more preferably above 0.30 ml/(g*mm), and even more preferably above 0.40 ml/(g*mm), as well as preferably below 0.80 ml/(g*mm). It is further preferred that the catalyst has a total pore volume of at least 0.23 ml/g and most preferably of at least 0.25 ml/g.

Preferably, the catalyst particles have a specific length of at least 0.10 mm, more preferably of at least 0.16 mm, and most preferably of at least 0.20 mm. The upper limit of the specific length preferably lies at 2.0 mm, more preferably at 1.0 mm, and most preferably at 0.6 mm.

5

The particles of the catalyst of the invention can have many different shapes, including spheres, cylinders, rings, and symmetric or asymmetric polylobes, for instance tri- and quadrulobes. Preferably, the catalyst particles have an average particle diameter of at least 0.5 mm, more preferably of at least 0.8
10 mm, and most preferably of at least 1.0 mm. The upper limit of the average particle diameter preferably lies at 10.0 mm, more preferably at 5.0 mm, even more preferably at 3.0 mm.

Preferably, the macropore volume ranges from 0.05 to 0.30 ml/g, more
15 preferably from 0.08 to 0.30 ml/g, and even more preferably from 0.08 to 0.25 ml/g.

The catalyst comprises a solid acid, such as a zeolite. Examples of zeolites contained in the catalyst of the invention are Y-zeolites, including H-Y-zeolites
20 and USY-zeolites, zeolite beta, MCM-22, and MCM-36. Preferably, the zeolite is Y-zeolite with a unit cell size in the range of 24.34 - 24.72 angstroms. More preferably, the zeolite is a Y-zeolite with a unit cell size in the range of 24.40-24.61 angstroms and a silica:alumina molar ratio in the range 7-18 and most preferably the zeolite is a Y-zeolite with a unit cell size in the range of 24.24-
25 24.58 angstroms and a silica:alumina molar ratio in the range 7.85-13.75.

As stated above, the catalyst comprises a hydrogenation function. A suitable hydrogenation function, e.g., comprises a Group VIII noble metal. The Group VIII noble metal preferably is contained in the catalyst in an amount of 0.01 - 2
30 wt%, and more preferably 0.1 - 1 wt%, calculated as metal and based on the

weight of the solid acid. Preferably, the Group VIII noble metal comprises palladium and/or platinum.

Preferably, the catalyst additionally comprises a matrix material. Examples of
5 suitable matrix materials are alumina, silica, titania, zirconia, clays, and mixtures thereof. Matrix materials comprising alumina are generally preferred.

Preferably, the catalyst of the invention comprises 2-98 wt% of the solid acid and 98-2 wt% of the matrix material, based on the total weight of the solid acid and matrix material present in the catalyst. More preferably, the catalyst
10 comprises 10 - 90 wt% of the solid acid and 90 - 10 wt% of the matrix material, based on the total weight of the solid acid and matrix material contained in the catalyst. Even more preferably, the catalyst comprises 20 - 80 wt% of the solid acid and 80 - 20 wt% of the matrix material, most preferably 50 - 80 wt% of the
15 solid acid and 20 - 50 wt% of the matrix material, based on the total weight of the solid acid and matrix material contained in the catalyst.

If desired, the solid acid can also comprise non-zeolitic solid acids such as silica-alumina, sulphated oxides, such as sulphated oxides of zirconium, titanium, or tin, mixed oxides of zirconium, molybdenum, tungsten, phosphorus, etc., chlorinated aluminium oxides or clays.
20

Preferably, the catalyst consists essentially of a hydrogenation function, a solid acid, and, optionally, a matrix material. More preferably, the catalyst consists
25 essentially of a zeolite, a Group VIII noble metal, and a matrix material. It is further preferred that the catalyst is essentially free of rare earth metals and/or Group VIII non-noble metals. Thus, most preferably, the catalyst of the invention consists essentially of a Group VIII noble metal compound, a zeolite, and a matrix, wherein

- (i) the zeolite consists essentially of oxidic compounds (oxides and hydroxides) of a Group III element, such as aluminium, and/or of a Group IV element, such as silicon, and, optionally, oxidic compounds of a Group I element, such as sodium, and/or of a Group II element, such as calcium, and/or of a Group V element, such as phosphorus, and, optionally, additionally ammonium and/or water, and
- (ii) the matrix is selected from the group of oxidic compounds of silicon, aluminum, titanium, zirconium, Group II metals or mixtures thereof.
- 10 The catalyst can be prepared by processes common to the industry. A typical process comprises the successive steps of
- (i) shaping, e.g., extruding the solid acid constituent, optionally after mixing it with a matrix material, to form particles,
- (ii) calcining the resulting particles, and
- 15 (iii) incorporating the hydrogenation function into the calcined particles by, e.g., impregnating the particles with a solution of a hydrogenation metal component and/or by (competitive) ion exchange.
- Alternatively, the catalyst can, e.g., be prepared by a process comprising the successive steps of
- 20 (i) incorporating the hydrogenation function into the solid acid constituent or into a mixture of the solid acid constituent and the matrix material,
- (ii) shaping, e.g., extruding the resulting material to form particles, and
- (iii) calcining the resulting particles.
- 25 The catalyst is particularly suitable for the alkylation of saturated hydrocarbons. The invention therefore further pertains to the use of the catalyst of the invention in the alkylation of these feedstocks. As stated above, this comprises the reaction of a saturated hydrocarbon with an olefin or olefin precursor in the presence of the catalyst of the invention to give highly branched saturated
- 30 hydrocarbons with a higher molecular weight.

Preferably, the hydrocarbon is a branched saturated hydrocarbon such as an isoalkane having 4 - 10 carbon atoms. Examples are isobutane, isopentane, isohexane or mixtures thereof, with isobutane being most preferred. The olefins
5 to be used in the alkylation process generally have 2 - 10 carbon atoms, preferably 2 - 6 carbon atoms, still more preferably 3 - 5 carbon atoms, and most preferably 4 carbon atoms. Most preferably, the alkylation process consists of the alkylation of isobutane with butenes.

10 As will be evident to the skilled person, the alkylation process can be applied in any suitable form, including fluidized bed processes, slurry processes, and fixed bed processes. The process may be carried out in a number of beds and/or reactors, each with separate olefin addition. In such a case, the process of the invention may be carried out in each separate bed or reactor.

15

Suitable process conditions are known to the skilled person. Preferably, an alkylation process as disclosed in WO 9823560 is applied. The process conditions applied in this process are summarized in the following Table:

	Temperature range [°C]	pressure range [bar]	molar ratio of saturated hydrocarbon to olefin
preferred	-40 - 250	1-100	5:1 - 5000:1
more preferred	0 - 150	10 - 40	50:1 - 1000:1
most preferred	60 - 95	15 - 30	150:1 - 750:1

20

Preferably, a regeneration technique as described in WO 9823560 is applied during the alkylation process. More in particular, during the alkylation process the catalyst is preferably subjected intermittently to a regeneration step by being contacted with a feed containing an aliphatic compound and hydrogen,
25 with said regeneration preferably being carried out at 90% or less, more preferably at 60% or less, even more preferably at 20% or less, and most preferably at 10% or less of the active cycle of the catalyst. The active cycle of

the catalyst is defined as the time from the start of the feeding of the alkylation agent to the moment when, in comparison with the entrance of the catalyst-containing reactor section, 20% of the alkylation agent leaves the catalyst-containing reactor section without being converted, not counting isomerisation
5 inside the molecule. Optionally, in this process, the catalyst can be subjected periodically to a high-temperature regeneration with hydrogen in the gas phase. This high-temperature regeneration is preferably carried out at a temperature of at least 150°C, more preferably at 175° - 600°C, and most preferably at 200° - 400°C. For details of this regeneration procedure, reference is made to WO
10 9823560, and in particular to page 4, lines 5 - 19 and page 9, line 13 through page 13, line 2.

The use of the catalyst of the present invention in the above alkylation process results in a high olefin conversion (amount of olefin in the feed that is converted
15 in the reaction), a high C5+ alkylate yield (weight amount of C5+ alkylate produced divided by the overall weight of olefin consumed) and a high octane number, while the amount of undesired C9+ by-products can be restricted and the catalyst's stability can thus be improved. For details in respect of these parameters, reference is made to WO 9823560.

20

The following characterization method was applied in the present invention:

The macropore volume as well as the total pore volume were determined via mercury intrusion on the basis of the Washburn equation

25

$$D = \frac{-4\gamma \cos\theta}{p}$$

with D being the pore diameter, p being the pressure applied during the measurement, γ being the surface tension, taken to be 480 dynes/cm, and θ

being the contact angle, taken to be 140°. In the present measurement, the pressure was varied over such a range that the measurement covered pores with a diameter in the range of 3.6 - 8000 nm.

- 5 The present invention will be further illustrated by way of the following examples:

General test procedure

10 A fixed-bed recycle reactor as described in WO 9823560 having a diameter of 2 cm was filled with a 1:1 volume/volume mixture of 38.6 grams of catalyst extrudates and carborundum particles (60 mesh). At the centre of the reactor tube a thermocouple of 6 mm in diameter was arranged. The reactor was flushed with nitrogen for 30 minutes (100 NI/hour). Next, the system was tested for leakages at elevated pressure, after which the pressure was raised to 21
15 bar and the nitrogen replaced by hydrogen (100 NI/hour). The reactor temperature was then raised to 200°C at a rate of 1°C/min. After 1 hour at 200°C the temperature was raised to 400°C at a rate of 1°C/min. After 1 hour at 400°C the reactor temperature was lowered to the reaction temperature, which is given in the Examples below.

20

The hydrogen stream was stopped with the attaining of the reaction temperature. Isobutane was supplied to the reactor at a rate of about 4,000 grams/hour. About 95 - 98% of the isobutane was fed back to the reactor. About 2 - 5% was drained off for analysis. Such an amount of isobutane was
25 supplied to the reactor to ensure a constant quantity of liquid in the system. When the system had stabilized, such an amount of cis-2-butene was added to it as to give a cis-2-butene-WHSV as given in the examples below (calculated on zeolite weight in the catalyst sample). The overall rate of flow of liquid in the system was maintained at about 4,000 g/h. The weight ratio of isobutane to cis-
30 2-butene in the reactor supply (without considering the unreacted material fed

back to the reactor) is given in the Examples below. The pressure in the reactor amounted to 21 bar.

Each time after 1 hour of reaction, the catalyst was regenerated by being washed with isobutane for 5 minutes, followed by 50 minutes of regeneration through being contacted with a solution of 1 mol% of H₂ in isobutane, and then being washed with isobutane for another 5 minutes (total washing and regeneration time 1 hour). After this washing step, alkylation was started again. The process conditions during the washing steps and the regeneration step were the same as the process conditions during the reaction step.

Unless specified otherwise, the catalytic performance was measured after a steady state was reached. The performance was characterized by the olefin conversion, the research octane number (RON), the C₅+ alkylate yield, and the weight percentage of undesired C₉+ by-products (excl. 2,2,5-trimethylhexane), calculated on C₅+ alkylate. The RON was determined as described on pages 13 and 14 of WO 9823560, the only exception being that the RON contribution of total C₉+ (excl. 2,2,5-trimethylhexane) was estimated to be 84 instead of 90. The C₅+ alkylate yield is defined as the weight amount of C₅+ alkylate produced divided by the overall weight of olefin consumed.

Example 1:

A catalyst of the invention was tested according to the above-described test procedure. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the unreacted material fed back to the reactor) was 20.

The reaction temperature was 70°C. The cis-2-butene-WHSV was 0.21 h⁻¹. The catalyst had the following properties:

Catalyst composition:

Solid acid: USY-zeolite

Solid acid amount: 70 wt% (based on the total weight of solid acid and matrix)

5 Hydrogenation metal: platinum

Hydrogenation metal amount: 0.34 wt%

Matrix: alumina

Matrix amount: 30 wt% (based on the total weight of solid acid and matrix)

10 Catalyst shape: cylindrical extrudates

Pore/particle characteristics:

Macropore volume: 0.17 ml/g

Specific length: 0.22 mm (average diameter: 1.0 mm, average length: 4 mm)

15 Macropore volume / specific length 0.77 ml/(g*mm)

Total pore volume: 0.36 ml/g

The catalytic performance is given in the Table below.

20

Example 2:

A catalyst with the same composition and shape as the catalyst of Example 1 was tested. The catalyst had a ratio between macropore volume and specific length of 0.64 ml/(g*mm) (macropore volume: 0.14 ml/g, specific length: 0.22 mm (average diameter: 1.0 mm, average length: 4 mm)). Its total pore volume was 0.35 ml/g. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the unreacted material fed back to the reactor) was 19. The reaction temperature was 70°C. The cis-2-butene-WHSV was 0.21 h⁻¹. The further test conditions were as described in Example 1. The catalytic performance is given in the Table below.

30

Example 3:

A catalyst with the same composition and shape as the catalyst of Example 1 was tested. It had a ratio between macropore volume and specific length of 0.41 ml/(g*mm) (macropore volume: 0.09 ml/g, specific length: 0.22 mm (average diameter: 1.0 mm, average length: 4 mm)). Its total pore volume was 0.27 ml/g. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the unreacted material fed back to the reactor) was 19. The reaction temperature was 70°C. The cis-2-butene-WHSV was 0.21 h⁻¹. The further test conditions were as described in Example 1. The catalytic performance is given in the Table below.

Example 4

A catalyst with the same composition and shape as that of Example 1 was tested. It had a ratio between macropore volume and specific length of 0.49 ml/(g*mm) (macropore volume: 0.17 ml/g, specific length: 0.35 mm (average diameter: 1.7 mm, average length: 4 mm)). Its total pore volume was 0.38 ml/g. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the unreacted material fed back to the reactor) was 26. The reaction temperature was 80°C. The cis-2-butene-WHSV was 0.19 h⁻¹. The further test conditions were as described in Example 1. The catalytic performance is given in the Table below.

Comparative Example A

A catalyst with the same composition and shape as the catalyst of Example 1 was tested. It had a ratio between macropore volume and specific length of 0.95 ml/(g*mm) (macropore volume: 0.21 ml/g, specific length: 0.22 mm (average diameter: 1.0 mm, average length: 4 mm)), which lies outside the claimed range. Its total pore volume was 0.50 ml/g. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the

unreacted material fed back to the reactor) was 30. The reaction temperature was 70°C. The cis-2-butene-WHSV was 0.21 h⁻¹. The further test conditions were as described in Example 1. The catalytic performance is given in the Table below.

5

Comparative Example B

A catalyst with the same composition and shape as the catalyst of Example 1 was tested. It had a ratio between macropore volume and specific length of 0.18 ml/(g*mm) (macropore volume: 0.04 ml/g, specific length: 0.22 mm
10 (average diameter: 1.0 mm, average length: 4 mm)). Its total pore volume was 0.19 ml/g, which lies outside the claimed range. The weight ratio of isobutane to cis-2-butene in the reactor supply (without considering the unreacted material fed back to the reactor) was 27. The reaction temperature was 80°C. The cis-2-butene-WHSV was 0.19 h⁻¹. The further test conditions were as described in
15 Example 1. As a steady state could not be reached, the catalytic performance was measured after 60 hours. The results are given in the Table below.

Discussion:

20 The catalytic performance of the catalysts of the above Examples is summarized in the Table below:

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Com. Ex. A	Com. Ex. B
Total pore volume [ml/g]	0.36	0.35	0.27	0.38	0.50	0.19
Macropore volume/ specific length [ml/(g*mm)]	0.77	0.64	0.41	0.49	0.95	0.18
Olefin conversion [%]	100	99.9	100	99.7	99.5	98.4
wt% C9+ (excl. 2,2,5- trimethyl-hexane), calc. on C5+ alkylate	5.3	6.4	5.0	6.1	13	10
RON (research octane number)	95.7	96.0	96.1	95.7	95.6	95.0
C5+ alkylate yield [%]	205	207	206	202	185	183

The performance of the catalysts of Comparative Examples A and B is significantly worse than that in Examples 1 - 4. More in particular, the C5+ alkylate yield is significantly lower than the corresponding yields of the catalysts according to the invention, whereas the weight percentage of undesired C9+ lies significantly above the corresponding values of the catalysts of Examples 1 - 4.

It is noted that this poor performance of the catalysts of Comparative Examples A and B is observed despite the fact that they were tested at conditions that should lead to a better catalytic performance than the conditions under which the catalysts of Examples 1 - 4 were tested. More in particular, the weight ratio between isobutane and cis-2-butene in Comparative Examples A and B is higher than in Examples 1 - 4. A higher weight ratio implies a lower amount of olefin in the reactor and thus a lower risk of excess olefin being able to react with the formed alkylate resulting in undesired C9+ products.

Claims

1. A catalyst suitable for use in the alkylation of hydrocarbons which comprises catalyst particles comprising a hydrogenation function and a solid acid, wherein the ratio between (i) the volume in catalyst pores with a diameter in the range of 40 - 8000 nm and (ii) the specific length of the catalyst particles is in the range of 0.01 - 0.90 ml/(g*mm) and wherein the catalyst has a total pore volume of at least 0.20 ml/g and the volume in the catalyst pores with a diameter in the range of 40-8000 nm is below 0.30 ml/g.
2. The catalyst according to claim 1 wherein the ratio between (i) the volume in catalyst pores with a diameter in the range of 40 - 8000 nm and (ii) the specific length of the catalyst particles is at least 0.20 ml/(g*mm).
3. The catalyst according to claim 1 or 2 wherein the catalyst has a total pore volume of at least 0.23 ml/g.
4. The catalyst according to any one of the preceding claims wherein the hydrogenation function consists essentially of a Group VIII noble metal.
5. The catalyst according to any one of the preceding claims wherein the solid acid is a Y-zeolite with a unit cell size in the range of 24.34 - 24.72 angstroms.
6. The catalyst according to claim 5 wherein the solid acid is a Y zeolite with a unit cell size in the range of 24.40-24.61 angstroms.
7. The catalyst according to claim 6 wherein the solid acid is a Y zeolite with a unit cell size in the range of 24.45-24.58 angstroms.

8. The catalyst according to any one of the preceding claims wherein the catalyst additionally comprises a matrix material.
- 5 9. The catalyst according to claim 8 wherein the matrix material comprises alumina.
10. The catalyst according to any one of the preceding claims wherein the catalyst is free of rare earth metals and Group VIII non-noble metals.
- 10 11. Use of the catalyst according to any one of the preceding claims for the alkylation of hydrocarbons.
- 15 12. Use of the catalyst according to any one of the claims 1-10 for the alkylation of saturated hydrocarbons.

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/EP 01/05845

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J35/10 B01J29/12 C07C2/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J C07C C10G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 23560 A (AKZO NOBEL NV) 4 June 1998 (1998-06-04) cited in the application the whole document	1-12
X	WO 98 42805 A (SHELL CANADA LTD ;SHELL INT RESEARCH (NL)) 1 October 1998 (1998-10-01) the whole document	1-10
X	EP 0 389 041 A (SHELL INT RESEARCH) 26 September 1990 (1990-09-26) example VII	1-8,10
X	EP 0 216 938 A (CATALYSTS & CHEM IND CO) 8 April 1987 (1987-04-08) the whole document	1-3,5-9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

24 September 2001

Date of mailing of the international search report

02/10/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Zuurdeeg, B

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/05845

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9823560	A	04-06-1998	NL 1004623 C2	28-05-1998
			AU 5750598 A	22-06-1998
			BR 9713441 A	01-02-2000
			CN 1238747 A	15-12-1999
			WO 9823560 A1	04-06-1998
			EP 0941211 A1	15-09-1999
			JP 2001504504 T	03-04-2001
			US 5986158 A	16-11-1999
WO 9842805	A	01-10-1998	US 6093672 A	25-07-2000
			WO 9842805 A1	01-10-1998
			EP 0968257 A1	05-01-2000
			US 6174430 B1	16-01-2001
EP 0389041	A	26-09-1990	AT 96053 T	15-11-1993
			AU 627004 B2	13-08-1992
			AU 5211790 A	27-09-1990
			BR 9001319 A	02-04-1991
			CA 2012663 A1	23-09-1990
			CN 1045763 A , B	03-10-1990
			DE 69003978 D1	25-11-1993
			DE 69003978 T2	10-02-1994
			DK 389041 T3	15-11-1993
			EP 0389041 A1	26-09-1990
			ES 2045751 T3	16-01-1994
			GR 3026117 T3	29-05-1998
			IE 63314 B	05-04-1995
			JP 2284650 A	22-11-1990
			JP 3159698 B2	23-04-2001
			NO 301068 B1	08-09-1997
			NZ 233026 A	27-08-1991
			RU 2007216 C1	15-02-1994
EP 0216938	A	08-04-1987	US 5106549 A	21-04-1992
			ZA 9002169 A	28-12-1990
			DE 3676266 D1	31-01-1991
			EP 0216938 A1	08-04-1987
			WO 8605715 A1	09-10-1986
			US 4789654 A	06-12-1988